

AMENDMENTS TO THE CLAIMS:

The following listing of claims replaces all prior listings, and all prior versions, of claims in the above-identified application.

LISTING OF CLAIMS:

1. (Previously presented) A circuit connecting material which is used to connect a first circuit member in which first circuit electrodes and first insulating layers are formed adjacent to each other on the main surface of a first circuit board, and a second circuit member in which second circuit electrodes and second insulating layers are formed adjacent to each other on the main surface of a second circuit board, with at least some of said insulating layers being formed such that these layers are thicker than said circuit electrodes on the basis of said main surface in at least one of said first and second circuit members,

wherein said material contains a bonding agent composition and conductive particles which have a mean particle size of 1 μm or greater but less than 10 μm , and a hardness of 1.961 to 6.865 GPa; and

said material exhibits, when subjected to a curing treatment, a storage elastic modulus of 0.5 to 3 GPa at 40°C, and a mean coefficient of thermal expansion of 30 to 200 ppm/°C at from 25°C to 100°C.

2. (Original) The circuit connecting material according to claim 1, wherein said conductive particles comprise a core body made of an organic polymer, and a

metal layer made of copper, nickel, a nickel alloy, silver or a silver alloy which is formed on the surface of said core body, and the thickness of said metal layer is 50 to 170 nm.

3. (Previously presented) The circuit connecting material according to claim 1, wherein said conductive particles comprise an outermost layer made of gold or palladium, and the thickness of said outermost layer is 15 to 70 nm.

4. (Previously presented) The circuit connecting material according to claim 1, wherein said bonding agent composition contains an epoxy resin and a latent curing agent for said epoxy resin.

5. (Previously presented) The circuit connecting material according to claim 1, wherein said bonding agent composition contains a radical-polymerizable substance, and a curing agent which generates free radicals when heated.

6. (Previously presented) The circuit connecting material according to claim 1, wherein the glass transition temperature is 60 to 200°C as a result of the curing treatment.

7. (Previously presented) The circuit connecting material according to claim 1, wherein the material further contains a film forming material.

8. (Original) The circuit connecting material according to claim 7, wherein said film forming material is a phenoxy resin.

9. (Previously presented) A film-form circuit connecting material which is formed by forming the circuit connecting material according to claim 1 into shape of a film.

10.-18. (Cancelled).

19. (Original) A method for manufacturing a circuit member connecting structure which comprises a first circuit member in which first circuit electrodes and first insulating layers are formed adjacent to each other on the main surface of a first circuit board, a second circuit member in which second circuit electrodes and second insulating layers are formed adjacent to each other on the main surface of a second circuit board, and a circuit connecting member which is disposed between the main surface of said first circuit member and the main surface of said second circuit member for connecting said first and second circuit members to each other, at least some of said insulating layers being formed so that these layers are thicker than said

circuit electrodes on the basis of the main surface of the circuit board in at least one of said first and second circuit members,

said method comprising the steps of:

interposing the film-form circuit connecting material according to claim 9 between the main surface of said first circuit board and the main surface of said second circuit board, and

curing said circuit connecting material by the application of heat and pressure via said first and second circuit members for thereby connecting said first circuit member and said second circuit member, so that said first circuit electrodes and said second circuit electrodes are electrically connected via said conductive particles.